

JET LAM GLOSS 12UM

Intended Application: The above product is a gloss polypropylene film, intended for use in either over-lamination or printing applications.

PROPERTIES

Item		Test Method	Unit	Result
Thickness		HSI Method	µm	12
Yield		-	m ² /kg	92.59
Tensile Strength	MD	ASTM D882	Kg / mm ²	14.2
	TD			30.5
Elongation at Break	MD	ASTM D882	%	158
	TD			58
Heat Shrinkage	MD	ASTM D1204	%	4.6
	TD			1.8
Surface Tension	IN	ASTM D2578	Dyne / cm	38
	OUT			38
Haze		ASTM D1003	%	1.6
Gloss Value	OUT	ASTM D2457	-	139.2
C.O.F	O/O	ASTM D1894	-	0.22

B&F Papers has endeavoured to ensure this information is correct; however, we do not accept liability for any error or omission. We reserve the right to update this information without prior notice.

Note: It is the user's responsibility to test all stock, prior to use, whether the product is suitable for intended application.

