

JET LAM MATT 30UM

Intended Application:	The above product is a matt polypropylene film, intended for use in either over-lamination or printing applications. Corona treatment – both sides treated.
------------------------------	--

PROPERTIES

Item		Test Method	Unit	Result
Thickness		HSI Method	µm	30
Tensile Strength	MD	ASTM D882	Kg / mm2	11.3
	TD			28.3
Elongation at Break	MD		%	190
	TD			51
Heat Shrinkage	MD	ASTM D1204	%	4.2
	TD			1.5
Wet Tension	IN	ASTM D2578	Dyne / cm	38
	OUT			42
Haze		ASTM D1003	%	81.2
Gloss Value	IN	ASTM D1894	-	
	OUT			16.1
C.O.F	I/I		-	
	O/O			0.21

B&F Papers has endeavoured to ensure this information is correct; however, we do not accept liability for any error or omission. We reserve the right to update this information without prior notice.

Note: It is the user's responsibility to test all stock, prior to use, whether the product is suitable for intended application.

