

## PMC FLUORO RED PP33F WG62

---

**Country of manufacture:** Thailand

---

**Applications:** General-purpose label designed for eye-catching applications such as instructional, promotional and POS label. It is advisable to test the product with the end-use conditions during the qualification to ensure it meets specific requirements.

### Product components

---

Face (FLUORO RED): One sided fluorescent coloured coated paper.

---

Adhesive (PP33F): General-purpose permanent adhesive, with very good water and aging resistance. Featuring excellent adhesion to low surface energy substrates.

---

Liner (WG62): Super calendered White Glassine paper.

---

## TECHNICAL SPECIFICATIONS

| Property | Grammage      | Thickness           |
|----------|---------------|---------------------|
| Face     | 72gsm         | 80 micron (3,1 mil) |
| Liner    | 60gsm         | 54 micron (2,1 mil) |
| Total    | 153 gsm, ±10% | 154 micron, ±10%    |

## ADHESIVE

| Property                        |                 |                                |        |         |
|---------------------------------|-----------------|--------------------------------|--------|---------|
| Initial Tack                    | Glass           | FTM 9                          | ≥ 12,5 | N/25 mm |
| Initial Tack                    | Stainless Steel | FTM 9                          | ≥ 12,0 | N/25 mm |
| Adhesion to                     | Stainless Steel | FTM 2 20<br>minute 90°<br>peel | ≥ 6,5  | N/25 mm |
| Minimum Service Temperature     |                 | -40 °C                         | -40 °F |         |
| Maximum Service Temperature     |                 | 120 °C                         | 248 °F |         |
| Minimum Application Temperature |                 | -5 °C                          | 23 °F  |         |

## CERTIFICATES

- US FDA 21 CFR 175.105 (Adhesive) for indirect food contact packaging and processing.
- European Toy Safety Legislation 88/278/EEC, CEN EN71, Part 3

B&F Papers has endeavoured to ensure this information is correct; however, we do not accept liability for any error or omission. We reserve the right to update this information without prior notice.

Shelf Life: From the date of manufacture 1 year in 22°C and RH 50%. These characteristics are average values supplied for guidance purposes.

**Note: It is the user's responsibility to test all stock, prior to use, whether the product is suitable for intended application.**

